

TECOSPHERE 200

TYPE	PERLITE MICROSPHERES
PRODUCTION FACILITY	IZMIR

PHYSICAL PROPERTIES

COLOR	WHITE
BRIGHTNESS %	85
BULK DENSITY	90 - 110 g/l
WATER REPELLENCY	NO
SPECIFIC GRAVITY	2.2 - 2.4
PH	6.50 - 7.00
OIL ABSORPTION (gr/100 cc)	45 - 65
Moisture %	max. 0,1
(d97) TOP CUT	190 - 200 μ m

TECOLITE MINERALS

FATIH MAHALLESİ, 1204. SK
NO:4 GAZİEMİR - İZMİR
www.tecoliteminerals.com
office@tecoliteminerals.com

CHEMICAL ANALYSES

SiO ₂	73 - 76
Al ₂ O ₃	11 - 13
K ₂ O	4.3 - 4.8
Na ₂ O	2.5 - 3.0
Fe ₂ O ₃	0.3 - 0.8
CaO	0.1 - 0.2
TiO ₂	< 0.1
MgO	< 0.1

GLOBAL PERLITA SL

PASAJE EL BOJAR, S/N
04738 Vicar Almeria
contact@globalperlita.com
www.globalperlita.com

FOR MORE INFORMATION PLEASE CONTACT OUR TEAM