



P 05

TYPE
PRODUCTION FACILITY

FINE PERLITE FILLER
Pionki, Poland

APPLICATIONS

Plasters, mortars, insulation
Reinforcement agent, cryogenic

PACKAGING

200 LT, 1500 LT, LOOSE

PHYSICAL PROPERTIES

COLOR
PARTICLE SIZE
DENSITY
THERMAL CONDUCTIVITY "4 °C"
Loss on Ignition %
PH %
SPECIFIC GRAVITY
Moisture %
SOFTENING POINT

WHITE
<1.0 mm
50-80 kg/m³
0.036 w/MK
<1.00
6.00-7.00
2.2 - 2.3
<0,1
1.100 °C

PRODUCTION FACILITY
Radomska 39,
26-670 Pionki
www.globalperlita.com
sales.pl@globalperlita.com

CHEMICAL ANALYSES

SiO ₂	74
Al ₂ O ₃	12
K ₂ O	4.7
Na ₂ O	3.9
Fe ₂ O ₃	0.6
CaO	0.1
TiO ₂	0.1
MgO	0.1

ISO 9001
ISO 14001
ISO 45001

FOR MORE INFORMATION PLEASE CONTACT TO OUR TEAM